

SL-TOOL[®] NewWhite

**Material-
Datenblatt ...**

SL-TOOL[®] NewWhite

ASTM Methode	Eigenschaft	Wert
	Density, fest	1,23g/cm ³
	Farbe	weiß
D638	Zugfestigkeit	~ 40-60 MPa
D638	Bruchdehnung	9-15%
D790	Biegemodul	~ 2400-2600 MPa
	Härte (Shore D)	85
	Formbeständigkeitstemp.	~ 50-60°C

robotmech Rapid Prototyping
Stössl GmbH
Bundesstr. 11 · A-6842 Koblach
Tel: ++43 55 23 / 510 31-0
e-mail: info@robotmech.com
www.robotmech.com