

Product Data Sheet

Name:	2170	
Specific Gravity:	1,2	
Product Colour:	yellowish	

Mechanical Properties

Flexural Strength	120	N/mm ²
Flexural Modulus	2690	N/mm ²
Tensile Strength	78,5	N/mm ²
Tensile Modulus	3530	N/mm ²
Elongation Break	6,5	%
Tear Strength		
Hardness	80 D	Shore

Thermal Properties

Heat Deflection Temp.	70	°C
Glass Transition Temp.	115	°C

Specific Properties

HDT after post curing process	95	°C
-------------------------------	----	----