

## Product Data Sheet

Name:	2181	
Specific Gravity:	1,1	
Product Colour:	yellowish	

## Mechanical Properties

Flexural Strength	62,1	N/mm <sup>2</sup>
Flexural Modulus	1395	N/mm <sup>2</sup>
Tensile Strength	14,7	N/mm <sup>2</sup>
Tensile Modulus	1635	N/mm <sup>2</sup>
Elongation Break	55	%
Tear Strength		
Hardness	76 D	Shore

## Thermal Properties

Heat Deflection Temp.	70	°C
Glass Transition Temp.	168	°C

## Specific Properties

HDT after post curing process	135	°C
-------------------------------	-----	----