

ASTM Method	Description	Value
	Density, solid	1,19g/cm ³
	Color	transparent
D638	Tensile Strength	~ 38-43 MPa
D638	Elongation at Break	13-24%
D790M	Flexural Modulus	~ 1940-2010 MPa
	Hardness (Shore D)	86
	Heat Deflection Temperature	~ 49°C