

ASTM Method	Description	UV Postcure	UV & Thermal Postcure
	Density, solid	1,37g/cm ³	N/A
	Color	light gray	
D638M	Tensile Strength	~ 47 MPa	~ 52 MPa
D638M	Elongation at Break	2,3%	~ 1,2%
D790M	Flexural Strength	~ 100 MPa	~ 125 MPa
D790M	Flexural Modulus	~ 4500 MPa	~ 6700 MPa
	Hardness (Shore D)	93	93
D648	Heat Deflection Temperature	~ 60 - 68°C	< 220°C
IEC 60243-1	Electric Strength	28,7 kV/mm	