

# SL-TOOL® Stonelike

ASTM Method	Description	UV Postcure	UV & Thermal Postcure
	Density, solid	1.37 g/cm <sup>3</sup>	N/A
	Color	light gray	
D638M	Tensile Strength	~ 47 MPa	~ 52 MPa
D638M	Elongation at Break	2.3 %	~ 1.2 %
D790M	Flexural Strength	~ 100 MPa	~ 125 MPa
D790M	Flexural Modulus	~ 4500 MPa	~ 6700 MPa
	Hardness (Shore D)	93	93
D648	Heat Deflection Temperature	~ 60-68 °C	< 220 °C
IEC 60243-1	Electric Strength	28.7 kV/mm	

Tolerances: ± 0.2 % (min. 0.2 mm)